


TEST RESULTS

Kedas Quality Control Department 	230x3.2x22.23 A24 PLUS T-BF metal cutting	230x3.2x22.23 C30 PLUS T-BF stone cutting	180x6.5x22.23 A30 PLUS T-BF metal grinding	115x1.6x22.23 AZ46 P-BF INOX st. steel cutting	115x3.2x22.23 A24 PLUS T-BF steel cutting	115x6.5x22.23 A30 PLUS T-BF metal grinding
Bursting test						
max. working speed [RPM]	6650	6650	8500	13300	13300	13300
bursting speed limit acc. To EN norm [RPM]	12441	12441	15902	23036	23036	23036
test result obtained [RPM]	13800	13100	16707	26240	24645	25980
percentage of EN norm	111,0%	105,0%	105,0%	114,0%	107,0%	113,0%
Side load test						
limit value [N]	50	50	290			
Breaking force [N]	103	131	512			
percentage of the limit	207,0%	262,0%	177,0%			
Impact test						
limit value [Nm]	2	2	5,4			
max. energy without breakage [Nm]	3	3,9	7,9			
max. energy without breakage for the limit	148,0%	196,0%	146,0%			



KEDAS[®]

Professional
Technology
Development

**THE EXPERTS
FOR HIGH QUALITY
CUTTING AND
GRINDING DISCS**

